



**The GreenShield® Company**

1600 N. Clinton Ave., #11  
Rochester, NY 14621

T 585-270-5282  
F 585-270-5791  
fleischer@greenshieldfinish.com

[www.greenshieldfinish.com](http://www.greenshieldfinish.com)

Repellency and Fluorine measurements of 100% Polyester Fabric  
GreenShield compared to the competition

<b>Description (all on 100 % PES)</b>	<b>WR</b>	<b>OR</b>	<b>ppm F Galbraith</b>	<b>ppm F Schwarzkopf</b>
GreenShield	7+	6	324	300
GreenShield	7+	6+	347	320
competitor 1: Nanosphere	5	5.5	1532	1300
competitor 2: Crypton	5	6.5	3800	2800
competitor 3: Nanotex	5	5.5	3600	2600

WR - water repellency per AATCC 118

OR - oil repellency per AATCC 193

Fluorine measured by two independent analytical companies